


STENCILMATE TECHNICAL DATA SHEET

0.004" STENCILMATE™ SEMI-PERMANENT PCB STENCILS



DESCRIPTION

StencilMate™ stencils are made from two layers of clear amber polyimide film with an adhesive backing. It is coated with an aggressive permanent acrylic adhesive and backed with a 50# Kraft release liner. The StencilMate stencils are pre-scored to allow for easy removal of the release liner

USES

Intended for use as a "remain-in-place" stencil for the application of solder paste or flux on printed circuit boards. The stencil material is designed to withstand high temperatures and harsh chemicals and .

Withstand surface mount circuit board processes. This high-performance material is designed for applications requiring excellent solvent and heat resistance. StencilMate™ stencils are designed with a permanent adhesive and they are not designed to be removed after being applied.

FEATURES

Excellent chemical, and heat resistance. The StencilMate™ stencil is dimensionally stable (no shrinkage) with a high-performance adhesive. StencilMate™ stencils have insulative properties in the material and adhesive. The minimum break through voltage (the voltage that will not pass through the polyimide) is 5000 volts. The voltage that will pass through the polyimide material is approximately 7000 volts.

PHYSICAL PROPERTIES

Description	Material	Convention Units	S.I. Units
Thickness	Polyimide	2.0 mils	51 microns
	Adhesive	2.0 mils	51 microns
	Liner (50#)	3.0 mils	75 microns
	Total	7.0 mils	177 microns
(Results in a solder print thickness of 0.004")			
Adhesive Performance	Stainless Steel	72.00 oz/in	790.00 N/m
	Fiberglass	28.98 oz/in	317.32 N/m
	Phenolic	29.97 oz/in	328.17 N/m
	Nylon	40.55 oz/in	444.01 N/m
(Adhesive performance after a 72 hour dwell)			
Service Temperatures	1-40 minutes	572°F	300°C
	2-4 minutes	617°F	325°C
	1-9 seconds	842°F	450°C
	1-3 seconds	1000°F	538°C

Application Temp.	Minimum	50°F	10°C																
Chemical Resistance	<p>Test should be conducted at room temperature after 24 hour dwell. Testing should consist of five cycles of 10 minute immersions in the specified chemical reagent followed by 30 minute recovery periods. Cotton swab rub prior to final immersion.</p> <table> <tr> <td>Household Cleaners</td> <td>No effect</td> </tr> <tr> <td>Mild Acid</td> <td>No effect</td> </tr> <tr> <td>Oil</td> <td>No effect</td> </tr> <tr> <td>Water</td> <td>No effect</td> </tr> <tr> <td>1 Part IPA, 1 Part Mineral Spirits</td> <td>No effect</td> </tr> <tr> <td>Terpene Defluxer</td> <td>No effect</td> </tr> <tr> <td>Toluene</td> <td>No effect</td> </tr> <tr> <td>Saponifier</td> <td>No effect</td> </tr> </table>			Household Cleaners	No effect	Mild Acid	No effect	Oil	No effect	Water	No effect	1 Part IPA, 1 Part Mineral Spirits	No effect	Terpene Defluxer	No effect	Toluene	No effect	Saponifier	No effect
Household Cleaners	No effect																		
Mild Acid	No effect																		
Oil	No effect																		
Water	No effect																		
1 Part IPA, 1 Part Mineral Spirits	No effect																		
Terpene Defluxer	No effect																		
Toluene	No effect																		
Saponifier	No effect																		
Storage Stability	Product should be stored at 70 degrees F (21 degrees C) and 40 – 50% relative humidity to ensure optimal performance.																		
Shelf Life	2 Years at the proper storage conditions.																		